


diamondspark Ni1 RC-SR

Seamless cored wire





Product Features	Product benefits	User benefits
» Fast freezing rutile slag system	Enhancing travel speed and arc stability in positional weldingeasy slag removal	» Productive positional welding» Automatic slag detachability
» Stable arc	» Welder-friendly» Smooth wetting» Low spatter	» Low defect rate» Good fatigue resistance» Less post weld cleaning
» Excellent feedability	» Dependable feedability» Low contact tip wear	» No starting defects» Increased arc time
» Seamless design	» Copper-coated seamless cored wire» Low-hydrogen weld metal	» Excellent current transfer» Resistance to moisture absorption» Low risk of HAC
» Designed chemistry	» Excellent mechanical properties» CTOD tested at -25 °C	» Guarantee of quality performance during Welding Procedure Qualifica- tion process

Seamless copper-coated rutile all-positional flux-cored wire from the diamondspark range for single- or multi-layer welding of low temperature steels up to 500 MPa yield strength and impact requirements down to -60 $^{\circ}$ C in the as welded and stress relieved conditions, using Ar-CO₂ shielding gas. CTOD tested at -25 $^{\circ}$ C. Alloyed with < 1 $^{\circ}$ C Ni to meet the NACE MR0175 requirement for SSC safe service in sour environments in oil and gas exploration and processing.

A single current/voltage setting can be applied for all welding positions. Its fast freezing slag enables deposition rates in positional welding up to three times as high as obtainable with any other manual arc welding process. Root runs are welded economically on ceramic weld metal support.

The seamless, copper-coated wire design adds sufficient stiffness and glide to overcome friction in liners, welding guns and contact tips. The copper-coating enhances current transfer between contact tip and wire resulting in a stable arc. Controlled wire cast and helix largely avoids "dog tailing", promoting straight, well positioned welds. The seamless design offers the best possible protection against moisture reabsorption during storage and use of the wires and thereby against hydrogen induced cracking. Diffusible hydrogen level is typically 2 - 3 ml / 100 g weld metal.





Typical applications

- » Constructions requiring stress relieve treatment
- » Vessels
- » Receivers



diamondspark Ni1 RC-SR

Classifications		Operating data	Allows welding with standard power sources	
EN ISO 17632-A	AWS A5.29/SFA-5.29	Welding positions	Polarity	Shielding gas
T50 6 1Ni P M21 1 H5	E81T1-Ni1M-JH4	**	DC+	EN ISO 14175: M21

Typical chemical composition, all weld metal, wt. %						
Shielding gas	С	Si	Mn	Ni		
M21	0.07	0.40	1.3	0.85		

Mechanical properties, all weld metal (single values typical)							
Shielding gas	Condition	Yield strength R _{p0.2%} MPa	Tensile strength R _m MPa	Elongation A ₅ %	CVN Impact to ISO-V KV J -40 °C	oughness -60°C	CTOD tested
	as welded	520 (≥500)	600 (560-690)	25 (≥20)	120	100 (≥47)	-25°C
M21	SR: 620°C/2h	500 (≥470)	580 (550-680)	29 (≥20)	120	90 (≥47)	
	SR: 620°C/6h	490 (≥470)	570 (550 - 680)	30 (≥20)	110	60 (≥47)	

Steels to be welded				
EN	ASTM			
\$355JR, \$355J0, \$355J2, \$450J0 \$355N-\$460N, \$355NL-\$460NL \$355M-\$460M, \$355ML-\$460ML \$460Q, \$500QL, \$460QL1, \$500QL1, \$755GH, \$755SNH, \$755NH, \$755NL-\$760NL1, \$755NH-\$760NH, \$755NL-\$760NL2, \$755NH-\$760NH, \$755NL-\$760NL2, \$755NL2-\$760NL2, \$755NL	A 350 Gr. LF2 A 516 Gr. 65, 70 A 572 Gr. 42, 50, 60, 65 A 573 Gr. 70	A 588 Gr. B, C, K A 633 Gr. A, C, D, E A 662 Gr. B, C A 678 Gr. B	A 707 Gr. L2, L3 A 841 Gr. A, B, C API 5 L: X42-X70 X52Q, X60Q, X65Q, X70Q	

Approvals

ABS, DNV-GL; LR, CE, TÜV

Overview spool types

Plastic spool \$200



Precision layer wound

Ø internal 52 mm

Dimensions:

Width

Available spool weight:

Available diameters: Ø external 200 mm 1.0 mm 1.2 mm

Wire basket spool BS300



Precision layer wound

Dimensions: Ø external 300 mm Ø internal 52 mm 100 mm Width

Available spool weight: 16 kg

Available diameters: 1.0 mm 1.2 mm 1.4 mm 1.6 mm

Welding Machines

For the best welding performance with our diamondspark flux-cored wires, we recommend our dedicated synergic lines available on voestalpine Böhler welding machines:

47 mm

Uranos 3200 PME; Uranos 4000 PME; Uranos 5000 PME; Uranos 3200 GSM; Uranos 4000 GSM; Uranos 5000 GSM.



